

Madras[®] by Galvolux

Exclusive decorative glass

Technical data sheet

Base product: patterned glass to EN 572-5.

Description and performance: the printed side is chemically satin-finished, opaque, very smooth, velvety to the touch. Effective visual obscuration and optimal light diffusion are the key properties. Thanks to its low porosity, it ensures greater resistance to fingerprints and easier cleaning than traditional sand-blasted glass.

Internal and external applications: building (façades, parapets...), windows & doors, partitions, furniture, shower-screens etc.

Fluido can also be supplied in the finishes:

- Fluido-T (transparent finish) - Art. 401011
- Fluido-M - Art. 401243

Sheet size:


- Fluido-T: 3350 x 1610 mm
- Fluido-M: 3210 x 1610 mm

Maximum possible dimensions:

- Fluido-T: 3300 x 1560 mm
- Fluido-M: 3300 x 1560 mm

Pattern direction: parallel to 3210 mm side.

Lines size:

12.5 ± 0.3 mm	
---------------	---

Thickness: 6 mm

Colour: clear

Compatible processing: Cutting, grinding, drilling, notching, varnishing, etc.

Processing such as tempering, layering and assembly in insulating glass are to be agreed.

Cleaning: care must be taken when installing the glass not to get putty, resin, sealants, etc., on the treated side. Each of these substances requires a specific solvent for removing traces from glass. For routine maintenance, use water and/or any of the commonly marketed glass detergents. Dry immediately with a clean cloth, preferably micro fibre.

Fluido



Fluido-M



Fluido-T

Colours and finishings in the photographs may look slightly different from those of the real products: we recommend that customers examine sample glass before choosing products.

GALVOLUX



QUALITY
AND WARRANTY
SINCE 1900

Galvolux SA

Via Strecce 1 - CH 6934 Bioggio

Tel. +41 91 610 55 11

info@galvolux.com

www.galvolux.com

Madras[®] by Galvolux

Exclusive decorative glass

Fluido

Faults acceptance limits:

Spot, linear and pattern (out of square, waviness, bow) faults stemming from production of base glass: as per Standard UNI EN 572-5 (patterned glass): 5. Quality requirements.

Faults stemming from chemical processing of glass:

Defect size/mm	Max no./sheet	average per 20 m ²
>0,6 e > 1,5	3	5
>1,5 e > 3,0	1	2
>3,0 e > 9,0	only with customer acceptance	only with customer acceptance



Colours and finishings in the photographs may look slightly different from those of the real products: we recommend that customers examine sample glass before choosing products.

GALVOLUX



QUALITY
AND WARRANTY
SINCE 1900

Galvolux SA

Via Strecce 1 - CH 6934 Bioggio

Tel. +41 91 610 55 11

info@galvolux.com

www.galvolux.com